| PRODUCT INFORMATION

3/8" COMB LIGHT

ADVANTAGES

• This material has been proved to

and thick panels are required

laminate, and coatings)

methods of attachment

• Easily apply face materials (veneer,

• Finish with a variety of edge options


• Rigid face material supports selected

• Optional skin thicknesses are available

be a great design solution for many applications where strong, lightweight 3/8 cell honeycomb core faced with 1/8 HDF.

SIZES AVAILABLE

- 3/4″x49x97
- 1″x49x97
- 1-1/4"x49x97
- 1-1/2″x49x97
- 1-3/4"x49x97
- 2″x49x97
- 3/4"x49x121
- 1″x49x121
- 1-1/4"x49x121
- 1-1/2″x49x121
- 1-3/4"x49x121
- 2″x49x121





TECHNICAL DATA

	MATERIAL THICKNESS									
	3/4″	1″	1-1/4"	1-1/2"	1-3/4″	2″				
SKIN THICKNESS	0.118″	0.118″	-	0.118″	0.118″	0.118″				
CORE THICKNESS	0.514″	0.764″	-	1.264″	1.514″	1.764″				
MAX SCREW WITHDRAWN FORCE, LBF	70	-	-	64	-	-				
MAX SCREW TENSILE FORCE, LBF	47	-	-	78	-	-				
MAX TENSILE STRENGTH, PSI	11	-	-	19	-	-				
COMP, STRENGTH @5% STRAIN, PSI	29	-	-	27	-	-				
MAX FLEXURE FORCE, LBF	71	-	-	120	-	-				
MODULUS OF RUPTURE, PSI	1886	-	-	870	-	-				
MODULUS OF ELASTICITY, PSI	214079		-	155483	-	-				
WEIGHT PER PANEL, LB** (49 x 97)	43	44	-	47	49	51				

PACKAGING QUANTITY PER SKID

	MATERIAL THICKNESS								
SHEET SIZE	3/4"	1"	1-1/4"	1-1/2"	1-3/4"	2"			
49 X 97	64	48	38	32	27	24			

* Testing conducted with Varianta Screw HC 013.30.900

** Actual measured weight may vary due to temperature and humidity. Weight provided is for comparative analysis only



| PRODUCT SPECIFICATION